

Table 10: Marine (Salt Water), Commodity Specification G Southern Pine Preservatives and Retentions¹

<i>End-Use Commodity</i>	AWPA Use Category (UC) Designation	Water-borne ²	Minimum Retention Requirements — Pounds per Cubic Foot (pcf)	
			Chromated Copper Arsenate (CCA) ³	Creosote (CR, CR-PS, CR-S)
<i>Piles, round</i>				
New Jersey & San Francisco Bay, North	5A		1.5	16.0 ¹⁰
Mid-Atlantic & San Francisco Bay, South	5B		2.5	20.0 ¹⁰
Florida, Gulf Coast, Puerto Rico, Hawaii	5C		2.5	20.0 ¹⁰
<i>Dual Treatment</i>				
First treatment	5B-C		1.0	
Second treatment	5B-C			20.0 ¹⁰
<i>Piles, sawn</i>				
<i>Dual Treatment</i>				
First Treatment	5A-C		1.5	
Second Treatment	5A-C			20.0 ¹⁰
<i>Glulam Timber¹⁸</i>	5A-C		2.5	25.0 ¹⁰
<i>Dual Treatment</i>				
First treatment	5A-C		1.5	
Second treatment	5A-C			20.0 ¹⁰
<i>Solid Sawn Lumber, Plywood, Bulkhead Sheathing & Ties, mine/bridge</i>	5A-C		2.5	25.0 ¹⁰
<i>Lumber/Timbers, Marine Out of Water Salt Water Splash, see Table 4</i>				