

**Table 6: Crossties and Switchties, Commodity Specification C
Southern Pine Preservatives and Retentions¹**

<i>End-Use Commodity</i>	AWPA Use Category (UC) Designation	Oilborne		
		Copper Naphthenate (CuN)	Pentachlorophenol - A&C (PCP)	Creosote (CR, CR-PS, CR-S)
<i>Crossties and Switchties</i>	4A-C	0.06	0.4	8.0

Minimum Retention Requirements — Pounds per Cubic Foot (pcf)